

CLAIMS

1. An adhesive rubber composition comprising 100 parts by weight of a rubber component and 0.1 to 3 parts by weight of a metal acetylacetonate having an average
5 particle size of 50 μm or less.

2. An adhesive rubber composition as claimed in claim 1, wherein said rubber component and metal acetylacetonate are mixed at a temperature of the highest temperature reached during mixing of 140°C or less.

10 3. An adhesive rubber composition as claimed in claim 1 or 2, where said metal acetylacetonate is cobalt (II) acetylacetonate or cobalt (III) acetylacetonate or a mixture thereof.

15 4. A tire using an adhesive rubber composition according to any one of claims 1 to 3.